A Govt. Regd. Test House =

Management System:

As per ISO/IEC 17025:2017

CORPORATE IDENTITY NUMBER: U71200WB2023PTC262957

CORPORATE OFFICE :

256A, M. G. Road, Purbasan, Thakurpukur, Kolkata - 700063

LABORATORY 1: 256A, M. G. Road, Purbasan, Thakurpukur, Kolkata - 700063 LABORATORY 2: 996, M. G. Road, Purbasan, Thakurpukur, Kolkata - 700063 Contacts: (033) 2497 1903, M (+91) 9830020628 / M (+91) 9432219707

E-mail: omegalabinfo98@gmail.com

	TEST REPO	Date: 06.06.2025		Page: 1 of 1
#Ref. No. #Issued To	SK/27/MY/2025/15 -02 (Physical)  : E-mail    Date: 24.05.2025  : M/s- Whitespice Chemicals India Pvt. Ltd.    41A, AJC Bose Road, 2 <sup>nd</sup> Floor, Suite-218,    Kolkata-700017	#Product Specification #Test Specification	: IS:1538 Reaf:20 : IS: 172 Reaf:20	7:1967
#Description of Sample(s)	Micro Silica (Silica Fume With Ultratech OPC 43 Cement) sample for the following tests.     Grade: 92+     Testing of Micro Silica.	#Seal / Stamp / Mark (if any)	: Sealed	
#Test Parameters	: Over Size Percent Retained on 45 micron IS Sieve & variation from average, Compressive strength, Specific Gravity & Consistency  This is to certify that the above sample (S) has/h	Sample received on Sample tested on	06.06.2	2025 to 2025

## PHYSICAL PROPERTIES

I. Building Infrastructure & Construction Materials:

Silica Fume:

Room Temperature: 27.6°C

Characteristics	Findings	Req. as per IS:15388-2003, Reaf:2022	
Over Size Percent Retained on 45 micron IS     Sieve (%)	4.5	10.00 Max	
Over Size Percent Retained on 45 micron IS     Sieve, variation from average (%)	0.45	5.00 Max	
Compressive strength at 7 days as percent of control sample, (%)	94.8	85.00 Min	
4. Specific Gravity	2.20	Not specified	
5. Consistency (%)	36.0	Not specified	

Remarks: The above submitted sample was duly tested as per relevant specification.

RBox Prepared by

♦♦♦♦ End of report ♦♦♦♦

SERVICES PVT. LTD.

S. K. CHATTERJEE DEPUTY TECHNICAL MANAGER (MECH.: BM/SR, NDT: BM-RCS) (AUTHORISED SIGNATORY

## Note:

- \* "#" denote the information are supplied by customer.
- \* Decision Rule applied as per OTSPL/QMSP-10 (wherever applicable)
- \* The test report relates to the Sample(s) submitted by Customer.
- \* Liability for return of sample(s) ceases after fifteen days unless adviced by concerned authority.
- \* The reproduction of the report except in full is invalid without written approval of the laboratory management.
- \* The test results referred in test report are based on observations & measurements under the stated environmental conditions.

Omegalab Testing Services Poli Lita